

ONGROFOL[®]-T THERMOFORM



Food grade films manufactured by Ongropack Ltd. are in compliance with European directives and regulations related to packaging materials intended to come into direct contact with food. We know that the excellent quality packing materials are an important factor for this industry, therefore we offer a wide range of ONGROFOL[®] THERMOFORM type films for thermoforming or vacuum forming applications.

Ongropack manufactures different types of ONGROFOL[®] THERMOFORM films to its Customers depending on application and processing, so we offer in our product range homo- and copolymer, normal and high impact resistance types, as well as some specialities like antistatic, anti block or high cold impact resistant films.

We offer a wide range of clear, translucent and opaque colours for a variety of food and technical packaging applications.

Our sales representatives are ready to give you advice on which of our range of films will be most suitable for your requirements.



Advantages:

- **excellent transparency**
- **wide range of colours and sizes**
- **excellent thermoformability**
- **special properties**
- **good resistance against different chemicals**

ONGROFOL[®]-T THERMOFORM

Technical data sheet T-type



Specifications	Unit	Value	Test Method
Width	mm	54 – 1550	OPV-002/2004
Thickness	µm	150 – 800	
Max. roll diameter			
54 — 150 (width)	mm	max. 400	
151 — 300 (width)		max. 600	
301 — 1550 (width)		max. 800	
Core size (internal diameter)	mm	76 , *152	
Tensile strength	MPa	min. 46	MSZ EN ISO 527:1999
Transparency	%	min. 86	MFF-411/1993
Vicat B	°C	74-76	MSZ EN ISO 306:1999

* from 300 mm width

Advice: For ensuring more advantageous processing conditions, films stored at temperatures below 10 °C should be allowed to acclimatize for at least 48 hours at a min. temperature of 20 °C before processing.

Table of formability

Type	Formability	Type	Formability
T-100	★	T-500	★★★★
T-200	★/	T-700	★★★★/
T-300	★★	T-900	★★★★★
T-400	★★/	★ good ★★★★★ excellent	



Typical applications:



- food packaging and technical packaging purposes
- forming of boxes and trays
- forming other contour forms

Related registrations:

OETI 1728/2005, 95/2002
2002/72, 1935/2004 78/142, 94/62
ISO 9001:2008, ISO14001:2004

 **Ongropack**
Ongropack Kft.

H-3704 Kazincbarcika, Pf.: 441 Telefon: 36 48 510 130, Fax: 36 48 310 005
E-mail: ongropack@ongropack.hu



www.ongropack.hu